



2601 Gas Hose



DESCRIPTION

Flexible, smooth, orange hose for liquefied petroleum gas (LPG), propane/butane, to EN ISO 3821/EN559.

In accordance with the new EN ISO 3821 and EN559, the hose is primarily for use in industrial welding and cutting applications. The 6.3 mm and 11.0 mm hoses are DG approved.

Please contact Codan for further information...

ADDITIONAL INFORMATION

Type no.	2601
Application	LPG / Propane / Butane
Standard length	50 metres
Working temp.	-30°C to 80°C
Inside compound	NBR
Inside colour	Black
Reinforcement	Polyester
Outside compound	EPDM
Outside colour	Orange
Standards	EN ISO 3821:2019
Std. branding	–

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
4,0	11,0	20	60	35	110	2601004000
5,0	11,4	20	60	40	116	2601005000
6,3	13,3	20	60	40	141	2601006000
8,0	15,0	20	60	40	173	2601008000
9,0	16,0	20	60	115	188	2601009000
10,0	17,0	20	60	50	203	2601010000
11,0	18,0	20	60	55	221	2601011000

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. The written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care, and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage of vulcanized Rubber Products).

The individual conditions of an application will affect the lifetime of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is complied with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use with incorrect media or use in environments outside the hose specification. Please contact Codan Rubber for individual product manufacturing tolerances.