



3311 AIR - WATER HOSE



Black, flexible universal hose for air and water.

High-quality EPDM inside and outside ensures good weather and ozone resistance in any environment.

For use in industrial applications for cold and hot water, compressed air and chemicals (acids excepted). Resistant to acetates and ketones.

Please contact Codan for further information.

ADDITIONAL INFORMATION

Type no.	3311
Application	Air – water hose
Standard length	50 metres
Working temp.	-40°C to 100°C
Inside compound	EPDM
Inside colour	Black
Reinforcement	Polyester
Outside compound	EPDM
Outside colour	Black
Standards	EN 694 (19 and 25 mm)
Std. branding	EN694:2014/A1 – 20 BAR WP

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
6,3	13,1	20	60	53	142	3311006000
8,0	14,8	20	60	60	169	3311008000
10,0	18,0	20	60	72	242	3311010000
13,0	20,8	20	60	85	286	3311013000
16,0	24,0	20	60	92	350	3311016000
19,0	27,4	20	60	100	482	3311019000
25,0	33,4	20	50	116	539	3311025000

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. The written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care, and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage of vulcanized Rubber Products).

© Codan Rubber Danmark A/S Valdemarshaab 1, DK-4600 Køge, Denmark

Tel. +45 56 64 64 Fax +45 56 64 65 48 Mail: info@codan.com www.codan.com

The individual conditions of an application will affect the lifetime of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is complied with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use with incorrect media or use in environments outside the hose specification. Please contact Codan Rubber for individual product manufacturing tolerances.